

**Plirox<sup>®</sup> A920**

**Type:** yellow pigment  
**Delivery Form:** solid (powder)  
**Chemical class:** synthetic ironoxide  $\alpha$ -FeOOH  
**Colour Index :** yellow 42 (77492)  
**CAS-Nr.:** 51274-00-1  
**REACH Registration No(s).:** 01-2119457554-33-0027

**Specification:** **color values and tinting strength against standard**

$\Delta E_{ab}$   $\leq 1,0$   
Tinting strength (%) 95 ~ 105

**Water soluble content (%)**  $\leq 0,3$   
**Sieve residue (0,045mm Sieve) (%)**  $\leq 0,3$   
**pH-value** 3-7  
**Content Fe<sub>2</sub>O<sub>3</sub> (%)**  $\geq 86$   
**Moisture (after production) (%)**  $\leq 1,0$   
**Particle shape** acicular  
**Oil absorption (ml / 100g)** 25-35  
**Tamped app. Density (g/ml)** 0,4-0,6

Test methods are based on ISO 1248 and ISO 787

**Standard packaging:** 25kg bag  
**Transport and storage:** Protect against weather. Store in a dry place and avoid extreme fluctuations in temperature.  
**Open packaging:** To prevent the absorption of air moisture close bags shortly after use.  
**Safety:** The product is not classified as dangerous under EU directives. It is not dangerous according to transport regulations.

Please observe the corresponding material safety data sheet, which contains information on product safety, ecology and handling. MSDS No.: **00004**



PIGMENT INTERNATIONAL GmbH & Co. KG  
D-36396 Steinau