

**PIrox® K3T**

<b>Type:</b>	black pigment
<b>Delivery Form:</b>	powder
<b>Chemical class:</b>	Synthetic mixed iron-manganese-oxide (Fe,Mn) <sub>2</sub> O <sub>3</sub>
<b>Colour Index :</b>	Pigment black 33
<b>EC-Nr.:</b>	269-056-3
<b>REACH Registration-No(s):</b>	01-2119457599-19-0008
<b>Specification:</b>	<b>color values and tinting strength against standard</b>

$\Delta E_{ab}$	≤ 1,0
Tinting strength (%)	95 - 105

<b>Water soluble content (%)</b>	≤ 0,5
<b>Sieve residue (0,045mm Sieve) (%)</b>	≤ 0,2
<b>pH-value</b>	5-8
<b>Content as Fe<sub>2</sub>O<sub>3</sub> (%)</b>	~ 70
<b>Moisture (after production) (%)</b>	≤ 0,6
<b>Particle shape</b>	spherical
<b>Oil absorption (ml / 100g)</b>	10-20
<b>Tamped app. Density (g/ml)</b>	1,1-1,5

Test methods are based on ISO 1248 and ISO 787

<b>Standard packaging:</b>	25kg bag
<b>Transport and storage:</b>	Protect against weather. Store in a dry place and avoid extreme fluctuations in temperature.
<b>Open packaging:</b>	To prevent the absorption of air moisture close bags shortly after use.
<b>Safety:</b>	The product is not classified as dangerous under EU directives. It is not dangerous according to transport regulations.

Please observe the corresponding material safety data sheet, which contains information on product safety, ecology and handling. MSDS No.: **00237**



PIGMENT INTERNATIONAL GmbH & Co. KG  
D-36396 Steinau

This information and any further advice are given in good faith but without any warranty, also if proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products to their suitability for the intended uses. The use and processing of our products to the final purpose are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.